

Cycolac* Resin EX58F Americas: COMMERCIAL

High impact ABS for sheet extrusion and blow molding applications. FDA food contact compliant.

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	400	kgf/cm ²	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	300	kgf/cm ²	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	3.1	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	31.6	%	ASTM D 638
Tensile Modulus, 5 mm/min	21200	kgf/cm ²	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	680	kgf/cm ²	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	22000	kgf/cm ²	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	44	cm-kgf/cm	ASTM D 256
Izod Impact, notched, -30°C	30	cm-kgf/cm	ASTM D 256
Instrumented Impact Total Energy, 23°C	380	cm-kgf	ASTM D 3763
THERMAL			
Vicat Softening Temp, Rate B/50	106	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	93	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	80	°C	ASTM D 648
CTE, -40°C to 40°C, flow	1.01E-04	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	1.04E-04	1/°C	ASTM E 831
Relative Temp Index, Elec	60	°C	UL 746B
Relative Temp Index, Mech w/impact	60	°C	UL 746B
Relative Temp Index, Mech w/o impact	60	°C	UL 746B
PHYSICAL			
Specific Gravity	1.03	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.6 - 0.8	%	SABIC Method
Melt Viscosity, 240°C, 100 sec-1	14000	poise	ASTM D 3825

¹ Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume rate are measured on injection moulded samples. All samples are prepared according to ISO 294.

² Only typical data for material selection purpose. Not to be used for part or tool design.
³ This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
⁴ Own measurement according to UL.
⁵ Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布，我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！

Cycolac* Resin EX58F
Americas: COMMERCIAL

TYPICAL PROPERTIES ¹	TYPICAL VALUE	UNIT	STANDARD
PHYSICAL			
Melt Volume Rate, MVR at 220°C/10.0 kg	4	cm ³ /10 min	ISO 1133
ELECTRICAL			
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	4	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	1	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	4	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	0	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating (3)	1.52	mm	UL 94

¹ Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 230C/50% relative humidity. All properties, except the melt volume rate are measured on injection moulded samples. All samples are prepared according to ISO 294.

² Only typical data for material selection purpose. Not to be used for part or tool design.
³ This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
⁴ Own measurement according to UL.
⁵ Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布, 我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！

Cycolac* Resin EX58F

Americas: COMMERCIAL

- Recommend initial lower temperatures settings to avoid material degradation/hang-up in die.
- Maintain melt temperature within processing range.

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
Extrusion Blow Molding		
Drying Temperature	80 - 90	°C
Drying Time	4 - 5	hrs
Drying Time (Cumulative)	24	hrs
Maximum Moisture Content	0.02	%
Melt Temperature (Parison)	215 - 230	°C
Barrel - Zone 1 Temperature	205 - 225	°C
Barrel - Zone 2 Temperature	205 - 225	°C
Barrel - Zone 3 Temperature	205 - 225	°C
Barrel - Zone 4 Temperature	205 - 225	°C
Adapter - Zone 5 Temperature	210 - 230	°C
Head - Zone 6 - Top Temperature	215 - 230	°C
Head - Zone 7 - Bottom Temperature	215 - 230	°C
Screw Speed	20 - 60	rpm
Extruder Feed Zone Temperature	60 - 75	°C
Mold Temperature	40 - 80	°C
Die Temperature	215 - 235	°C
Sheet Extrusion		
Drying Temperature	80 - 95	°C
Drying Time	4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	215 - 260	°C
Barrel - Zone 1 Temperature	170 - 200	°C
Barrel - Zone 2 Temperature	180 - 220	°C
Barrel - Zone 3 Temperature	190 - 225	°C
Barrel - Zone 4 Temperature	200 - 240	°C
Adapter Temperature	205 - 250	°C
Die Temperature	205 - 250	°C
Roll Stack Temp - Top	90 - 95	°C

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅

备注：以上原料物性数据由厂家发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！

Cycolac* Resin EX58F
Americas: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
Sheet Extrusion		
Roll Stack Temp - Middle	95 - 105	°C
Roll Stack Temp - Bottom	100 - 105	°C

- Purge material from extruder prior to shutdown.
- For extended downtime, lower barrel, head and die temperatures to 95°C (200°F).

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume rate are measured on injection moulded samples. All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.
3) This rating is not intended to reflect hazards presented this or any other material under actual fire conditions.
4) Own measurement according to UL.
5) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布, 我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！