

Elastollan® 690 A 10U

Thermoplastic Polyurethane Elastomer (Polyester)

Elastogran GmbH

General	
Material Status	• Commercial: Active
Availability	• Europe
Additive	• UV Stabilizer
Appearance	• Clear/Transparent
Forms	• Pellets

Physical	Nominal Value	Unit	Test Method	
Density	1.21	g/cm ³	ISO 1183	
Mechanical		Nominal Value	Unit	Test Method
Tensile Stress (Break)	52.0	MPa	ISO 527-2	
Tensile Strain (Break)	540	%	ISO 527-2	
Elastomers		Nominal Value	Unit	Test Method
Tear Strength	95	kN/m	ISO 34-1	
Hardness		Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	90		ISO 868	

Additional Information
Note: These properties were tested in accordance with the DIN test standard.
Abrasion Loss, DIN 53516: 40 mm³

Notes

¹ Typical properties: these are not to be construed as specifications.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由IDES发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！