

# Elastollan® LP 9215

## Thermoplastic Polyurethane Elastomer (Polyester)

### Elastogran GmbH

General				
Material Status	• Commercial: Active			
Availability	• Europe			
Additive	• Plasticizer			
Forms	• Pellets			
Physical		Nominal Value	Unit	Test Method
Density		1.17	g/cm <sup>3</sup>	ISO 1183
Mechanical		Nominal Value	Unit	Test Method
Tensile Stress (Break)		40.0	MPa	ISO 527-2
Tensile Strain (Break)		850	%	ISO 527-2
Elastomers		Nominal Value	Unit	Test Method
Tear Strength		45	kN/m	ISO 34-1
Hardness		Nominal Value	Unit	Test Method
Shore Hardness (Shore A)		62		ISO 868
Additional Information				
Note: These properties were tested in accordance with the DIN test standard.				
Abrasion Loss, DIN 53516: 50 mm <sup>3</sup>				

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 [www.kedisujiao.com](http://www.kedisujiao.com)

备注：以上原料物性数据由IDES发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！