

# Elastollan® S 60 D 50

## Thermoplastic Polyurethane Elastomer (Polyester)

### Elastogran GmbH

General				
Material Status	• Commercial: Active			
Availability	• Europe			
Forms	• Pellets			
Physical		Nominal Value	Unit	Test Method
Density		1.25	g/cm <sup>3</sup>	ISO 1183
Mechanical		Nominal Value	Unit	Test Method
Tensile Modulus		250	MPa	ISO 527-2
Tensile Stress (Break)		45.0	MPa	ISO 527-2
Tensile Strain (Break)		500	%	ISO 527-2
Elastomers		Nominal Value	Unit	Test Method
Tensile Stress				ISO 37
100% Strain		18.0	MPa	
300% Strain		34.0	MPa	
Tear Strength		170	kN/m	ISO 34-1
Compression Set				ISO 815
23°C		40	%	
70°C		50	%	
Impact		Nominal Value	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-30°C		6.0	kJ/m <sup>2</sup>	
23°C		No Break		
Hardness		Nominal Value	Unit	Test Method
Shore Hardness (Shore D)		60		ISO 868
Additional Information				
Note: These properties were tested in accordance with the DIN test standard.				
Stress at 20% elongation, DIN 53504: 15 Mpa				
Abrasion Loss, DIN 53516: 25 mm <sup>3</sup>				

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 [www.kedisujiao.com](http://www.kedisujiao.com)

备注：以上原料物性数据由IDES发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！